

ITEM	GS 033/T	Test Method
	(OLII)	
QUALITY	NBR/SBR	
COLOUR	BLACK	
SPECIFIC GRAVITY	1,5 gr/cm3	ISO 2781 : 1998
SHORE HARDNESS	70 +/-5	ISO 7619 : 1986
TEAR STRENGHT	Mpa min. 5	ISO 37 : 1994
ELONGATION AT BREAK	300%	ISO 37 : 1994
TEAR RESISTANCE	15 kn/m	ISO 34-1 : 1994
TEMPERATURE	- 20°C + 80°C	

The above given information should be considered as a guide but cannot regarded as an engagement from our side.