

DATA SHEET

EUROFOAM

EUROGOM

ITEM	GS 036/D	Test Method
QUALITY	EPDM/SBR	
COLOUR	BLACK	
SPECIFIC GRAVITY	1,5 gr/cm ³	ISO 2781 : 1998
SHORE HARDNESS	60/65	ISO 7619 : 1986
TEAR STRENGTH	Mpa min.5	ISO 37 : 1994
ELONGATION AT BREAK	300%	ISO 37 : 1994
TEAR RESISTANCE	18 kn/m	ISO 34-1 : 1994
OZONE TEST (50pphm)	NO CRACK	ASTM D 3395 at 40 °C
TEST AT 100°C x 72 hours		hardness +10% tensile strength +13% elongation -45%
TEMPERATURE	- 40°C + 85°C	
VERY GOOD RESISTANT TO OXIGEN	CHANGE VOLUME LESS THEN 10%	

The above given information should be considered as a guide but cannot regarded as an engagement from our side.